

Derby Dry HD Cement

- A dry, high duty, heat setting, silicate bonded mortar.
- Service temperature limit is 2900 ° F.
- Used to lay high duty fireclay brick and insulating firebrick.
- Good bonding strength.
- Can be mixed to stiff troweling, regular troweling or dipping consistency.

Maximum recommended service temperature.....2900⁰F
Material Required for Estimating.....450 lbs. / M 9” equiv.
Mixing Water Required.....8-9 qts. / 75 lb.

Chemical Analysis:

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	CaO	MgO	
36.6%	57.5%	1.2%	1.7%	0.5%	0.4%	

Please contact: Phone; (518) 701-6722

Email; sales@ceramaterials.com

For pricing; www.ceramaterials.com

