



Ceramic Paper Properties

Specs	Standard Grade	High-Purity Grade	Zirconia Grade
Color	White	White	White
Maximum Use Limit	2300°F	2300°F	2552°F
Continuous Use Limit	2012°F	2012°F	2462°F
Density (PCF)	10-13	10-13	10-13
Organic Content (%)	< 5%	< 5%	< 5%
Tensile Strength (PSI)	75-90	30-40	75-90
Break Strength (PSI)	10-15	10-15	10-15
Thermal Conductivity @ 600°C (1112°F) @ 800°C (1472°F) @ 1000°C (1832°F)	W/mk (Btu in./hr/ft ² °F) 0.08 (0.55) 0.12 (0.80) 0.18 (1.25)	0.08 (0.55) 0.11 (0.75) 0.16 (1.15)	0.08 (0.55) 0.11 (0.76) 0.17 (1.18)

Grade	Standard Grade	Premium Grade	Zirconium Grade
Al ₂ O ₃	45-46%	47-49%	39-40%
SiO ₂	51-52%	50-52%	42-43%
ZrO ₂	-	-	15-17%
Fe ₂ O ₃	< 1.0%	0.2%	0.2%
K ₂ O+Na ₂ O	≤ 0.5%	0.2%	0.2%
LOI	< 10%	< 10%	< 10%

Please contact:

Jerry Weinstein

(518) 701-6722

Email: jerryw@ceramaterials.com

CeraMaterials is a major supplier of multiple lines of refractory materials which include ceramic fiber materials, ceramic filters, graphite sheets and foils, fiberglass products, refractories and carbon felt & board products.