



CERAMATERIALS

"Your One Stop Shop for Thermal Processing"

Derby Dry HD Cement

- A dry, high duty, heat setting, silicate bonded mortar.
- Service temperature limit is 2900° F.
- Used to lay high duty fireclay brick and insulating firebrick.
- Good bonding strength.
- Can be mixed to stiff troweling, regular troweling or dipping consistency.

Maximum recommended service temperature:
2900° F Material required for estimating: 450
lbs/ M9" equiv. Mixing water required: 8-9
qts/75 lbs

Chemical Analysis:

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	CaO	MgO
36.6%	57.5%	1.2%	1.7%	0.5%	0.4%