

# Carbon Tow (Hexcel IM-7)

HexTow® IM7 carbon fiber is a continuous, high performance, intermediate modulus, PAN based fiber available in 12,000 (12K) filament count tows. This fiber has been surface treated and can be sized to improve its interlaminar shear properties, handling characteristics, and structural properties. It is suggested for use in weaving, prepregging, filament winding, braiding, and pultrusion.

The unique properties of HexTow® IM7 fiber, such as higher tensile strength and modulus, as well as good shear strength, allow structural designers to achieve both higher safety margins for both stiffness and strength critical applications.

IM7-G 12k (0.25%) carbon fiber has been qualified to NMS 818 Carbon Fiber Specification (NCAMP). This allows customers to call out an industry standard, aerospace grade carbon fiber without the need to write and maintain their own specification.

Typical Fiber Properties	U.S. Units	SI Units
Tensile Strength		
6K	800 ksi	5,515 MPa
12K	820 ksi	5,655 MPa
Tensile Modulus (Chord 6000-1000)	40.0 Msi	276 GPa
Ultimate Elongation at Failure		
6k	1.9%	1.9%
12K	1.9%	1.9%
Density	0.0643 lb/in <sup>3</sup>	1.78 g/cm <sup>3</sup>
Weight/Length		
6K	12.5 x 10 <sup>-6</sup> lb/in	0.223 g/m
12K	25.0 x 10 <sup>-6</sup> lb/in	0.446 g/m
Approximate Yield		
6K	6,674 ft/lb	4.48 m/g
12K	3,337 ft/lb	2.24 m/g
Tow Cross-Sectional Area		
6K	1.94 x 10 <sup>-4</sup> in <sup>2</sup>	0.13 mm <sup>2</sup>
12K	3.89 x 10 <sup>-4</sup> in <sup>2</sup>	0.25 mm <sup>2</sup>
Filament Diameter	0.203 mil	5.2 microns
Carbon Content	95.0%	95.0%
Twist	Never Twisted	Never Twisted

Typical HexPly 8552 Composite Properties	U.S. Units	SI Units	Test Method
0° Tensile Strength	395 ksi	2,723 MPa	ASTM D3039
0° Tensile Modulus	23.8 Msi	164 GPa	
0° Tensile Strain	1.6%	1.6%	
0° Flexural Strength	270 ksi	1,862 MPa	ASTM D790
0° Flexural Modulus	22.0 Msi	152 GPa	
0° Short Beam Shear Strength	18.5 ksi	128 MPa	ASTM D2344
0° Compressive Strength	245 ksi	1,689 MPa	ASTM Mod. D695
0° Compressive Modulus	21.2 Msi	146 GPa	
0° Open Hole Tensile Strength	62 ksi	427 MPa	ASTM D5766
0° Open Hole Compressive Strength	48.8 ksi	336 MPa	ASTM D6484
90° Tensile Strength	16.1 ksi	111 MPa	ASTM D3039
Fiber Volume	60%	60%	

(518) 701-6722

sales@graphimaterials.com

www.graphimaterials.com

